



newUP Grade AsahiKASEI

Mechanical Purging Compound for Injection Molding & Extrusion

Packaging



newUP Grade is available in :
20kg bags (pictured above)



PICTURED: Close-up of newUP Grade

Product Safety

Refer to SDS
for more information

Key Measurements

Specific Gravity	0.87~0.94
Softening Point	154°C to 164°C



Visit our website
for
• News/Events
• SDS
• Training videos

<https://www.asahi-kasei.co.jp/asaclean/en/>

Description & Benefits

- **Special grade for PP**
 - * Excellent compatibility to PP
 - * Can be ideally used for PE as well
- **Low residue purge**
 - * Ideal for transparent or unreinforced application
 - * Excellent chaser to newEX grade to ensure maximum cleaning with minimum residue
- **Fast color/material change of PP**
- **Optimized for shutdown & sealing**
- **Mechanical purge (No chemical reaction)**

Usage Information

Temperature Range :	170°C to 300°C
Applicant:	Injection Molding - including hot runners Extrusion - profile, sheet, blown film, compounding
Types of Resin:	Purging to and from PP-based resins within the processing temperature range.
Amount of Purge:	Typically 1-2 system capacities (actual amount depends on degree of contamination)
Minimum Clearance:	Requires 0.5 mm clearance for hot runner gates and extrusion dies; for extrusion screen packs, nothing finer than 100-mesh screen packs may be used.
Soak Time:	Not required

* Detailed instruction may vary to optimize your purging process.

Physical & Chemical Properties

Pellet color:	Milky white
Base resin:	Olefinic resin
Inorganic additives:	Not intentionally used
Stability:	Stable under normal temperatures
Reactivity:	Non-reactive under normal handling and storage conditions
Conditions to avoid:	Do not exceed recommended temperature range. Do not allow ASACLEAN newUP Grade to reside in barrel for more than 30 minutes at temperatures higher than 280°C